

# SikaForce®-7720 L105

## Non-sagging assembly adhesive

### Technical Product Data

Properties	Component A SikaForce®-7720 L105	Component B SikaForce®-7050
Chemical base	Polyols, filled	Isocyanate derivatives
Colour (CQP <sup>1</sup> 001-1)	White	Brown
Colour mixed	White	
Cure mechanism	Poly addition	
Density (CQP 006-5)	1.6 g/cm <sup>3</sup> approx.	1.2 g/cm <sup>3</sup> approx.
Density mixed (calculated)	1.5 g/cm <sup>3</sup> approx.	
Solids content	100%	100%
Mixing ratio	by volume 100 : 25 by weight 100 : 19	
Viscosity <sup>2</sup> (CQP 538-2)	Brookfield - RVT 7/2.5 1'000 Pa·s approx.	Brookfield - RVT 2/50 35 Pa·s approx.
Viscosity (mixed)	Brookfield - RVT 7/10 200 Pa·s approx.	
Application temperature	15 - 30°C (60 - 85°F)	
Pot-life <sup>2</sup> (CQP 536-3)	105 min. approx.	
Open time <sup>2</sup> (CQP 590-1)	105 min. approx. (see diagram 1)	
Press time <sup>2</sup> (CQP 590-1)	230 min. approx. (see diagram 1)	
Shore D hardness <sup>2</sup> (CQP 537-2)	80 D approx.	
Tensile strength <sup>3</sup> (CQP 545-2 / ISO 527)	15 N/mm <sup>2</sup> approx.	
Elongation at break <sup>3</sup> (CQP 545-2 / ISO 527)	6% approx.	
Shelf life (storage between 10 and 30°C)	12 months	6 months

<sup>1)</sup> CQP = Corporate Quality Procedure    <sup>2)</sup> 23°C (73°F) / 50% r.h.    <sup>3)</sup> Curing conditions: 21 days at 23°C (73°F) / 50% r.h.

### Description


Sika-Force®-7720 L105 is the base part of a two component polyurethane adhesive used with Sika-Force®-7050 hardener. SikaForce®-7720 L105 is manufactured in accordance with ISO 9001 / 14001 quality assurance system and the responsible care program.

### Product Benefits

- Thixotropic
- Gap filling
- Solvent free
- Can also be used with SikaForce®-7010 hardener

### Areas of Application

SikaForce®-7720 L105 can be used for assembly of profiles and sandwich constructions of e.g. glass fibre reinforced polyester, wood, metal, ceramic materials and pre-treated plastic materials. This product is suitable for professional experienced users only. Test with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.



### Cure Mechanism

The curing of SikaForce®-7720 L105 takes place by a chemical reaction of the two components. Higher temperatures speed up and lower temperatures slow down the curing process.




Diagram 1: Press-, open- and application time SikaForce®-7720 L105

### Chemical Resistance

In case of chemical or thermal exposure, we recommend a project related testing.

Consult the Technical Service Department of Sika Industry for advice.

### Method of Application

#### Surface preparation

Prepare the substrates for bonding to ensure optimal adhesion and strength. Ensure to have a clean and dry surface. Certain substrates might require a physical or chemical pre-treatment. The type of pre-treatment must be determined by tests.

Advice on specific applications is available from the Technical Service Department of Sika Industry.

#### Application

Coat weights between 150 and 350 g/m<sup>2</sup> are recommended depending on the substrates to be bonded. The specific coat weight for a given substrate combination is to be determined by tests.

The procedure for manual application is as follows: Stir the base part thoroughly before use, add the hardener in the given ratio and stir constantly until a homogeneous mixture is obtained. Apply with trowel before reaching half of the pot life and join parts together within the open time.

Further details can be obtained from the Technical Service Department of Sika Industry.

For automated applications contact the System Engineering Department of Sika Industry.

#### Pressing

An adequate bonding pressure to obtain a void-less contact between the substrates and adhesives is necessary. The specific pressure is, however, dependent on the core material and must be determined by tests. The pressure must always be below the maximum compressive strength of the core. After starting the press process do not release the pressure until the press time has elapsed.

#### Removal

Uncured SikaForce®-7720 L105 may be removed from tools and equipment with SikaForce®-7260 Cleaner. Once cured, the material can only be removed mechanically. Hands and exposed skin should be washed immediately using Sika® Handclean towels or a suitable industrial hand cleaner and water. Do not use solvents!

#### Storage conditions

SikaForce®-7720 L105 has to be kept between 10°C and 30°C in a dry place. Do not expose it to direct sunlight or frost. After opening of the packaging, the content must be protected against humidity. Minimum temperature during transportation is -20°C for maximum 7 days.

### Further Information

Copies of the following publications are available on request:

- Material Safety Data Sheets

### Value Bases

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

### Health and Safety Information

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Material Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

### Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Further information available at:

[www.sika.ch](http://www.sika.ch)  
[www.sika.com](http://www.sika.com)

Sika Schweiz AG  
Business Unit Industry  
Tüffenwies 16  
CH-8048 Zurich  
Switzerland  
Tel. +41 58 436 40 40  
Fax +41 58 436 55 30

